International Journal of Scientific Research and Engineering Development-– Volume 9 Issue 6, Nov – Dec 2026
Available at www.ijsred.com

RESEARCH ARTICLE OPEN ACCESS

Optimization of Metal Additive Manufacturing Parameters

Shendage D.E.
(Assistant professor, Adusl's Technical Campus, chas Ahilyanagar)
Email: Shendagedattatray06@gmail.com

----------**********----------

Abstract
Laser powder bed fusion (LPBF) enables complex metallic components but is highly sensitive to interacting process parameters. This paper develops a research framework for optimizing laser power, scan speed, layer thickness, and hatch spacing for SS 316L components. A four-factor Box–Behnken response-surface design is proposed to quantify main, quadratic, and interaction effects on relative density, porosity, surface roughness, yield strength, ultimate tensile strength, elongation, and microhardness. Volumetric energy density is retained only as a supporting descriptor because identical energy values can arise from physically different power–speed combinations. The expected process window is bounded by lack-of-fusion defects at insufficient melting and keyhole, evaporation, and spatter-related instability at excessive thermal input. Multi-response desirability optimization is recommended to maximize density and strength while minimizing porosity and roughness. The proposed methodology provides a machine-, powder-, and geometry-specific route for parameter qualification and industrial control.

Keywords— additive manufacturing, laser powder bed fusion, SS 316L, process optimization, porosity, surface roughness, mechanical strength, response surface methodology.

----------**********----------

I. INTRODUCTION

Metal additive manufacturing has progressed from rapid prototyping to production of high-value aerospace, medical, energy, tooling, and industrial components. In LPBF, a focused laser selectively melts successive powder layers. The ability to manufacture internal channels, lattice structures, and consolidated assemblies is accompanied by sensitivity to thermal history, powder condition, gas flow, machine calibration, scan strategy, and part geometry.

Laser power, scan speed, layer thickness, and hatch spacing are among the most influential controllable variables. Power determines delivered thermal input, scan speed sets laser–material interaction time, layer thickness controls the volume that must be melted and the vertical discretization, and hatch spacing governs overlap between neighboring tracks. Their combined effect is often summarized as volumetric energy density, $E_v = P/(vht)$, where P is power, v is scan speed, h is hatch spacing, and t is layer thickness. However, energy density cannot replace the four individual factors because power–speed pairs with the same E_v can produce different melt-pool geometry, recoil pressure, cooling rate, and stability [1]–[3].

A. Problem Statement

A productivity-focused parameter set may sacrifice density and surface integrity, while a density-only optimum can increase residual stress, distortion, evaporation, and build time. A statistically designed, multi-response investigation is therefore required to locate a robust operating window rather than a single maximum-energy condition.

B. Objectives

- Quantify main and interaction effects on density and porosity.
- Determine effects on Ra and Sa surface roughness.
- Measure yield strength, ultimate tensile strength, elongation, and microhardness.
- Fit quadratic response models and test adequacy using analysis of variance.
- Identify and validate a constrained multi-response optimum.

II. LITERATURE REVIEW

A. Laser Power and Scan Speed

Low power or high scan speed can yield discontinuous tracks and incomplete bonding. Increasing input initially improves wetting and remelting. At excessive power or low speed, a deep vapor depression may form and collapse, creating keyhole pores; evaporation, denudation, and spatter can also destabilize the powder bed. Density therefore normally has an interior maximum [1], [2].

B. Layer Thickness and Hatch Spacing

Thicker layers raise deposition rate but require deeper penetration to fuse the current layer to the previously solidified material. If penetration is inadequate, interlayer lack-of-fusion increases. Hatch spacing determines track overlap. Excessive spacing leaves unmolten channels, while very small spacing increases remelting, heat accumulation, residual stress, and production time. Optimum spacing must be related to measured melt-pool width rather than selected independently.

C. Surface and Mechanical Performance

LPBF surface texture originates from layer stepping,

 ©IJSRED: All Rights are Reserved

adhered particles, contour instability, spatter redeposition, and local overmelting. Unstable contour melt pools have been associated with increased roughness, but the relationship between melt-pool width and roughness is not universal across alloys and platforms [4]. Mechanical performance depends on pore fraction, defect morphology, texture, microstructure, residual stress, and orientation. Irregular lack-of-fusion defects are especially damaging because they behave as crack-like stress concentrators.

D. Research Gap

Many investigations hold layer thickness constant, vary only two or three parameters, or optimize a single response using energy density alone. The present framework retains four independent factors and jointly considers consolidation, surface finish, strength, ductility, and productivity.

III. MATERIALS AND METHODS

A. Material and Equipment

Gas-atomized SS 316L powder with a nominal 15–45 µm particle-size range is proposed. Chemistry, oxygen content, morphology, reuse history, and size distribution should be documented. Fabrication should use an inert-atmosphere LPBF system with calibrated laser power and focus, controlled argon flow, documented build-plate preheat, and a constant 67° interlayer scan rotation.

TABLE I PROPOSED FACTOR LEVELS

Low	Centre
150	200
700	900
0.030	0.040
0.080	0.100

D. Quality Assurance

- Calibrate laser power, focus, oxygen sensor, recoater alignment, and test equipment.
- Record powder lot, sieve condition, reuse count, blend ratio, moisture exposure, and storage history.
- Record specimen XY location, interruptions, alarms, oxygen history, and recoater events.
- Use independent confirmation builds and retain abnormal-build data with a documented sensitivity analysis.

IV. OPTIMIZATION FRAMEWORK

A. Multi-response Desirability

Each response is converted to a desirability between zero and one. Density and porosity receive highest priority, followed by mechanical acceptance, roughness, and productivity. The overall criterion is the weighted geometric mean. Physical constraints must stop the optimizer from choosing a statistically attractive but unstable boundary condition.

TABLE III ILLUSTRATIVE OPTIMIZATION GOALS

The ranges in Table I are starting values, not universal settings. Preliminary single-track and cube trials must exclude combinations that cause severe balling, overheating, recoater interference, or obvious lack of fusion. Over the proposed space, nominal E_v ranges from about 22.7 to 148.8 J/mm3.

B. Experimental Design

A four-factor Box–Behnken design is recommended because it estimates a second-order model without placing all factors simultaneously at extreme corners. The design contains 24 edge-midpoint combinations. Five replicated centre points provide 29 parameter combinations and an estimate of pure error. Run order should be randomized, and multiple plates should be treated as statistical blocks.

For each response Y, the model is $Y = \beta_0 + \Sigma\beta_i x_i + \Sigma\beta_{ii} x_i Z + \Sigma\beta_{ij} x_i x_j + \varepsilon$. Model terms are tested using ANOVA at $\alpha = 0.05$ while preserving hierarchy. Adjusted RZ, predicted RZ, root-mean-square error, lack of fit, and residual diagnostics are reported.

C. Specimens and Measurements

TABLE II RESPONSE MEASUREMENT PLAN

nse	Method	
ty	Archimedes + section	
ty	Optical/SEM analysis	Area, size, shap
ess	Profilometer/optical	Ra, Rz, Sa, Sz
ess	Vickers HV0.5/HV1	
le	ASTM E8/E8M	
ure	Optical/SEM/EBSD	Pools, grains,

*The roughness target is project-specific and should be replaced by the functional surface requirement.

B. Validation Criteria

At least three independent confirmation builds should be produced at the predicted optimum and one nearby robust setting. Observed means should meet engineering limits and fall within 95% model prediction intervals. Robustness is assessed by small controlled parameter shifts representing normal machine variation.

V. EXPECTED RESULTS AND DISCUSSION

This section states literature-grounded hypotheses, not fabricated experimental results. At insufficient input, irregular lack-of-fusion pores are expected along layer and hatch boundaries. Increasing power or decreasing speed should initially improve fusion. At excessive input, deep keyholes, vaporization, spatter, and rounded pores are expected. The density response should therefore be concave, with the optimum inside a stable conduction-mode window

 ©IJSRED: All Rights are Reserved



Density cubes, surface coupons, and subsize tensile specimens should be distributed across the build plate. Surface measurements must distinguish up-skin, sidewall, and down-skin. Metallographic thresholding should be standardized and manually checked. Tensile orientation, strain measurement, fracture location, and heat-treatment condition must be reported.
remain sensitive to contour stability and adhered powder. A high-energy unstable surface melt pool may worsen roughness through swelling, balling, and redeposited spatter.

Strength and ductility should improve as lack-of-fusion defects are suppressed. Nevertheless, a density-only optimum may not maximize elongation or fatigue resistance because small defects, texture, residual stress, and microstructure remain active. Stress relief and heat treatment must be held constant during comparison.

TABLE IV EXPECTED INTERACTION MECHANISMS

Interaction	Expected
Power × speed	Melt regime and peak temperature
Power × layer	Penetration for deposited volume
Speed × hatch	Fusion and overlap at high throughput
Power × hatch	Track width versus overlap
Layer × hatch	Volume consolidated per scan length

VI. INDUSTRIAL IMPLEMENTATION

Industrial transfer should follow seven gates: baseline machine verification, safe-region screening, randomized DOE, constrained optimization, independent confirmation, formal qualification, and production monitoring. The released specification should identify machine and software version, laser calibration, powder limits, core and contour parameters, atmosphere, preheat, scan strategy, orientation, supports, stress relief, surface finishing, acceptance tests, and reaction limits.

A. Principal Failure Modes

- Lack of fusion: low power, high speed, thick layers, or wide hatch spacing.
- Keyhole porosity: excessive power or low speed with vapor-depression instability.
- Balling: unstable tracks, poor wetting, excessive speed, or unsuitable powder/atmosphere.
- Recoater interference: curling, raised edges, spatter accumulation, or inadequate supports.
- Low ductility: irregular defects, residual stress, inclusions, or elevated powder oxygen.

VII. LIMITATIONS

The proposed ranges are illustrative and require machine-specific screening. Build orientation, contour settings, powder reuse, preheat, gas flow, support design, heat treatment, and geometry are controlled but can materially affect results. Archimedes density cannot reveal defect morphology or location; metallography and, for critical components, X-ray computed tomography should supplement it. Tensile performance does not guarantee fatigue performance, and fitted models must not be extrapolated outside the investigated region.

Constrained multi-response desirability and independent validation should produce a robust, machine- and powder-specific parameter specification rather than a universal energy-density value.

ACKNOWLEDGMENT

The author acknowledges the published work of researchers and standards organizations that established the scientific and measurement basis for this proposed study.

REFERENCES

I. DETAILED PROCESS-PARAMETER MECHANISMS

A. Laser Power and Absorbed Energy

Laser power controls the rate at which optical energy is delivered to the powder bed, but the absorbed fraction depends on wavelength, powder chemistry, particle size, oxidation, packing density, and the changing geometry of the melt pool. At low power, the melt pool may be too shallow to penetrate the powder layer and remelt the previously solidified track. The resulting discontinuities form planar lack-of-fusion defects. When power is increased within a stable range, wetting, track continuity, and metallurgical bonding improve. At very high power, metal evaporation produces recoil pressure and a deep vapor depression. Instability or collapse of this depression can trap gas and form keyhole pores. Therefore, power should be optimized together with speed, focus position, beam diameter, and platform-specific optical calibration.

B. Scan Speed and Melt-Pool Lifetime

Scan speed determines the exposure time of a location beneath the laser. Excessively high speed shortens interaction time and may create narrow, discontinuous tracks, particularly when paired with thick layers or wide hatch spacing. Excessively low speed increases heat accumulation, vaporization, spatter, and local distortion. Speed also affects solidification rate and thermal gradient, which influence cellular spacing, epitaxial grain growth, and texture. A stable speed range

 ©IJSRED: All Rights are Reserved

should produce continuous tracks without strong swelling, balling, or excessive plume activity.

C. Layer Thickness and Hatch Spacing

Layer thickness changes both productivity and the penetration requirement. A 50 µm layer contains about 67% more deposited thickness than a 30 µm layer and normally requires a larger melt volume. If energy and overlap are not adjusted, incomplete interlayer bonding becomes likely. Hatch spacing governs lateral overlap. For example, a 100 µm hatch used with a 140 µm effective track width produces approximately 29% geometric overlap, whereas a 120 µm hatch gives approximately 14% overlap. Actual overlap should be calculated from metallographically measured track width rather than nominal laser spot diameter.

D. Coupled Operating Window

The four parameters should be interpreted as a coupled operating window. Low power, high speed, thick layers, and wide hatch spacing all move the process toward lack of fusion. High power, low speed, thin layers, and narrow hatch spacing move the process toward heat accumulation, evaporation, and keyholing. A robust setting lies between these boundaries and remains acceptable when normal machine variation changes laser output, powder spreading,

I. MEASUREMENT AND CHARACTERIZATION PROTOCOLS

A. Density and Porosity

Archimedes density provides a rapid bulk estimate but should be supported by polished cross-sections because equal density values can contain very different defect populations. Samples should be cleaned, dried, weighed with a calibrated balance, and measured using a documented immersion medium and temperature. Metallographic sections should be taken in planes parallel and perpendicular to the build direction. Image thresholding should use consistent illumination, magnification, polishing, and segmentation rules. Report pore fraction, equivalent diameter, maximum defect size, aspect ratio, circularity, and location.

B. Surface Texture

Surface measurement should distinguish profile parameters such as Ra and Rz from areal parameters such as Sa and Sz. The instrument, stylus radius or optical objective, sampling length, evaluation length, filtering method, and measurement direction must be stated. Measurements parallel and perpendicular to layer bands may differ. Down-facing surfaces should be analyzed separately because support contact, dross formation, and local overhang angle can dominate roughness.

C. Tensile and Hardness Testing

Tensile specimens should follow ASTM E8/E8M-compatible proportions and use a calibrated extensometer for yield and elongation measurement. Orientation relative to the build direction must be reported. At least three valid specimens are recommended for each confirmation condition. Fracture surfaces should be examined to determine whether failure initiated at lack-of-fusion defects, inclusions, surface notches, or internal pores. Vickers hardness traverses should use consistent load, dwell, spacing, and distance from the surface.

D. Microstructure and Residual Stress

Optical microscopy and scanning electron microscopy should document melt-pool boundaries, cellular solidification structure, inclusions, and defects. Electron backscatter diffraction can quantify grain orientation, texture intensity, and local misorientation. For applications sensitive to distortion or cracking, residual stress should be measured by X-ray diffraction or another validated method. Heat treatment, machining, and stress relief must be controlled because these operations can change hardness, residual stress, grain structure, and tensile response.

TABLE VI MINIMUM MEASUREMENT REPORTING

Characteristic
Density
Porosity
Roughness
Tensile
Hardness
Microstructure

be built without recoater interference or gross lack of fusion.

A. Box–Behnken Run Structure

The recommended four-factor Box–Behnken design contains 24 edge-midpoint combinations and five centre-point repetitions. Centre points should be distributed throughout the run order instead of being grouped. If more than one build plate is required, plate should be introduced as a block. Each plate should contain repeated reference coupons fabricated with the current qualified machine parameter set. These reference coupons help separate experimental parameter effects from drift in powder condition, atmosphere, recoating, or laser calibration.

TABLE V EXAMPLE EXPERIMENTAL CONTROL PLANENT

B. Replication and Sample Allocation

At least three density coupons should be associated with each parameter condition when build area permits. Tensile testing is more resource-intensive; therefore, tensile specimens may be concentrated at centre points, predicted optimum settings, process-window boundaries, and selected interaction conditions. Surface coupons should provide separate vertical, up-skin, and down-skin faces. All coupons should carry traceable identifiers that link the specimen, build file, machine log, powder history, metallographic section, and test result.

C. Randomization and Blocking

 ©IJSRED: All Rights are Reserved

Randomization reduces bias from systematic drift, while blocking accounts for known nuisance sources. If run order cannot be fully randomized because several coupons share one parameter region, the limitation should be stated and plate position should be included in the statistical model. Confirmation builds should be performed on different days and, preferably, after routine machine start-up to represent realistic repeatability.

I. STATISTICAL MODELLING AND MODEL DIAGNOSTICS

A. Model Fitting

Each response should initially be fitted with a hierarchical second-order model containing four linear terms, six two-factor interactions, and four quadratic terms. Hierarchy means that a linear term remains when its interaction or square is retained, even if the linear p-value is not individually significant. Model reduction should be based on engineering logic, residual behavior, and predictive performance rather than p-values alone. Responses expressed as percentages may require a logit or other variance-stabilizing transformation when values cluster near a boundary.

B. Analysis of Variance

ANOVA should report model sum of squares, residual error, lack of fit, pure error, degrees of freedom, mean squares, F-statistics, and p-values. A significant model is not sufficient by itself. Lack of fit should be compared with pure error, and adjusted RZ should be considered together with predicted RZ. A large difference between adjusted and predicted RZ indicates overfitting, influential observations, or inadequate reproducibility.

C. Residual and Influence Diagnostics

Residual-versus-fitted plots should show no funnel, curvature, or systematic grouping. A normal probability plot should be reviewed for strong tail departures. Run-order residuals can reveal drift associated with powder aging, thermal history, or oxygen excursions. Leverage, externally studentized residuals, and Cook's distance should identify influential runs. An observation should not be removed merely because it is inconvenient; removal requires a documented assignable cause such as specimen damage, test invalidity, or a confirmed build anomaly.

D. Optimization and Uncertainty

Desirability optimization should use explicit lower and upper limits for density, porosity, roughness, strength, elongation, and productivity. The optimum should be selected from a broad high-desirability region rather than a narrow numerical peak. Prediction intervals should accompany all predicted responses. Monte Carlo propagation or bootstrap resampling may be used to estimate the probability that a candidate setting satisfies every engineering constraint under expected parameter variation.

I. INDUSTRIAL QUALIFICATION AND PROCESS CONTROL

A. Qualification Strategy

Industrial qualification should freeze the complete manufacturing route rather than only four laser parameters. The controlled definition should include machine identity, software version, laser calibration, optical condition, powder specification, sieve practice, reuse limit, atmosphere, gas flow, plate preheat, scan strategy, core and contour parameters, support design, orientation, stress relief, support removal, machining, cleaning, and inspection. Any material change should be evaluated through a formal change-control process.

B. Monitoring and Reaction Limits

Routine process monitoring should include oxygen concentration, build-plate temperature, filter condition, recoater events, laser calibration status, and powder history. Where available,

C. Control Coupons and Traceability

Witness coupons should be placed at representative build locations and linked to the same powder, atmosphere, thermal cycle, and post-processing route as the production parts. Coupon type and frequency should reflect application risk. Traceability records should link the finished component to the machine, build file, parameter revision, powder lot, operator, build log, heat-treatment batch, inspection results, and nonconformance decisions.

D. Transfer between Machines

A parameter set should not be transferred solely by matching VED. Machines may differ in beam diameter, beam profile, calibration, scanning dynamics, gas flow, recoater design, preheat, and thermal boundary conditions. Transfer should begin with laser and atmosphere verification, followed by single-track comparison, density cubes, microstructure, tensile testing, and confirmation of critical dimensions. The receiving machine should be qualified using its own evidence.

TABLE IX PRODUCTION CONTROL ITEMS

Item
Laser output
Oxygen
Powder reuse
Recoat quality
Build log
Witness coupons

I. MICROSTRUCTURE–PROPERTY RELATIONSHIPS

A. Solidification Structure

LPBF 316L commonly develops fine cellular or columnar substructures because of rapid solidification and repeated directional heat flow. Melt pools partially remelt previous layers, promoting epitaxial grain growth across layer boundaries. Parameter changes alter thermal gradient, solidification velocity, cellular spacing, and crystallographic texture. These changes can affect yield strength and anisotropy even when measured density is similar.

 ©IJSRED: All Rights are Reserved

A. Defect Morphology and Fracture

Defect shape is as important as defect fraction. Rounded gas pores have lower stress concentration than sharp, irregular lack-of-fusion defects of comparable area. Planar defects oriented perpendicular to the tensile axis can cause early fracture. Consequently, optimization based only on mean density may overlook a small population of critical flaws. Maximum defect size, projected area, aspect ratio, and orientation should be included when linking porosity to tensile or fatigue behavior.

B. Influence of Heat Treatment

Stress-relief heat treatment can reduce residual stress and improve dimensional stability, but it may also change dislocation structure, cellular segregation, hardness, and tensile properties. Solution treatment may reduce the as-built cellular structure and modify texture-related behavior. All parameter conditions should therefore be compared in the same material state. If both as-built and heat-treated behavior are required, heat treatment should be treated as a separate experimental factor or a clearly separated study phase.

C. Mechanical Performance Interpretation

Yield strength reflects the combined influence of fine solidification structure, dislocation density, texture, and residual stress. Ultimate tensile strength and elongation are strongly affected by defect population and fracture path. A high-density condition may still show low elongation if the specimen contains a single large lack-of-fusion flaw or severe surface notch. For fatigue-critical applications, polished specimens and X-ray computed tomography should be considered after identifying the dense process window.

TABLE VIII
EXPECTED STRUCTURE–PROPERTY LINKS

Observation
Fine cellular spacing
Strong columnar texture
Irregular planar pores
Rounded small pores
Surface-connected defect
High tensile residual stress

PRODUCTIVITY, COST, AND SUSTAINABILITY CONSIDERATIONS

A. Build-Rate Metrics

A useful approximate volumetric build rate is the product of scan speed, hatch spacing, and layer thickness. At 900 mm/s,

0.10 mm hatch spacing, and 0.04 mm layer thickness, the nominal scanned volume is 3.6 mm3/s before contour passes, recoating time, jumps, acceleration, and support exposure are considered. Increasing speed, hatch spacing, or layer thickness can raise nominal productivity, but each change reduces the available fusion margin unless power and overlap are adjusted.

B. Cost Trade-offs

Total cost includes machine time, powder, inert gas, labor, support material, heat treatment, inspection, machining, rejected builds, and qualification testing. A parameter set that shortens exposure time but increases roughness can shift cost into machining and finishing. Similarly, a dense but very slow setting may be unattractive for production. Multi-response optimization should therefore include a secondary productivity or cost response after minimum quality requirements have been satisfied.

C.Powder Utilization

Powder reuse can improve material utilization, but repeated handling may change oxygen level, particle-size distribution, morphology, flowability, and contamination risk. Reuse policy should define sieving, blending, storage, sampling, and rejection limits. Powder history should be incorporated as a block or controlled variable when studying process parameters. Results obtained with virgin powder should not automatically be assumed to apply after many reuse cycles.

D.Energy and Waste Reduction

Stable parameter windows reduce failed builds, scrapped parts, rework, and unnecessary post-processing. Near-net-shape production can reduce machining waste, but supports, powder preparation, gas supply, heat treatment, and long machine operation remain relevant. Sustainability assessment should therefore consider energy per accepted component rather than energy per build alone. First-pass yield, build utilization, support fraction, machining allowance, and powder recovery are practical indicators for industrial improvement.

TABLE X ILLUSTRATIVE PRODUCTIVITY INDICATORS

Indicator
Nominal build rate
First-pass yield
Powder utilization
Support fraction
Post-process time
Specific energy

I. FUTURE WORK AND EXTENDED RESEARCH OPPORTUNITIES

A.Fatigue and Defect Tolerance

The proposed tensile program should be followed by fatigue testing because small surface-connected or lack-of-fusion defects may control cyclic life even when tensile properties are acceptable. Future work can compare as-built, machined, and polished surfaces; vertical and horizontal orientations; and stress-relieved versus solution-treated conditions. Defect-size measurements from X-ray computed tomography can be combined with fracture mechanics or Kitagawa–Takahashi-type assessments.

B. In-situ Monitoring and Machine Learning

Layerwise images, photodiode signals, melt-pool emission, acoustic data, and machine logs can be aligned with coupon location and destructive

 ©IJSRED: All Rights are Reserved

measurements. Supervised models may then classify lack-of-fusion, keyhole, or nominal regions. Such models require careful separation of training and validation builds, control of class imbalance, and independent testing on new powder lots or machines. Monitoring should supplement, not prematurely replace, qualified inspection methods.

C. Robust and Adaptive Optimization

A future robust-design study can intentionally vary laser calibration, oxygen level, powder reuse, plate position, and preheat within normal operating limits. The objective would be to identify settings with low response sensitivity rather than only the best nominal mean. Bayesian optimization or sequential response-surface methods may reduce the number of experiments by selecting new runs based on model uncertainty and expected improvement.

D. Geometry-Specific Process Development

Bulk cubes do not represent every production feature. Thin walls, overhangs, lattice struts, internal channels, sharp corners, and large cross-sections experience different heat flow and may require separate contour, up-skin, down-skin, or support parameters. Future qualification should include representative geometry coupons and critical feature measurements. Local parameter adaptation may improve quality but increases software, traceability, and validation requirements.

E. Closing Research Perspective

The most defensible optimization strategy combines physical process understanding, statistically designed experiments, validated metrology, uncertainty analysis, and independent confirmation. The resulting parameter specification should identify not only a nominal optimum but also the acceptable operating region, control variables, monitoring expectations, and limits of applicability. This approach supports repeatable LPBF production while avoiding the misleading assumption that one energy-density value can define quality across all machines, powders, and geometries.

CONCLUSIONS

LPBF quality cannot be optimized by maximizing laser power or minimizing scan speed in isolation. Power and speed establish melt-pool input and stability, while layer thickness and hatch spacing define the material volume and overlap to be consolidated. The process window is bounded by lack of fusion at insufficient melting and keyhole or evaporation-related instability at excessive input. A four-factor Box–Behnken design combined with density, porosity, roughness, hardness, tensile, and microstructural measurements can quantify nonlinear and interaction effects efficiently.

VIII. EXPERIMENTAL EXECUTION PLAN

A. Preliminary Screening

Before the response-surface experiment, single-track scans should be produced on a solid 316L substrate and on a representative powder layer. Track continuity, width, height, penetration, and visible spatter should be measured. Parameter combinations that produce severe balling, substrate damage, deep keyholes, or unstable tracks should be excluded. Small cubes should then confirm that the retained combinations can Metal Additive Manufacturing is an advanced manufacturing technology in which components are produced by adding material layer by layer based on a three-dimensional CAD model. Unlike conventional manufacturing processes, such as casting, forging, and machining, additive manufacturing provides greater design flexibility and enables the fabrication of complex geometrical structures. Among various metal additive manufacturing techniques, Laser Powder Bed Fusion is widely investigated for producing metallic components. In layer by layer until the required component is manufactured.

SS316L stainless steel is an important material for metal additive manufacturing because of its corrosion resistance, strength, and industrial applicability.

However, achieving the required component quality remains a significant challenge. The final properties of LPBF-manufactured components depend on several interacting process parameters, including:

- Laser power
- Scanning speed
- Hatch spacing
- Layer thickness
- Scanning strategy
- Build orientation

The selection of appropriate process parameters is essential for controlling melt-pool behaviour, porosity, microstructure, surface quality, and mechanical performance.

Therefore, the present research focuses on optimizing the process parameters of LPBF to improve the quality and performance of SS316L components using experimental and statistical optimization techniques.

Research literature confirms that these process variables have significant and interdependent effects on the final component quality.

ScienceDirect+2

5. Problem statement

The quality of metal components manufactured through LPBF is highly dependent on the selection of appropriate process parameters. Improper combinations of laser power, scanning speed, hatch spacing, and layer thickness may result in porosity, incomplete fusion, poor surface finish, and inconsistent mechanical properties.

Although several studies have investigated individual process parameters, obtaining a suitable combination of parameters that simultaneously improves surface roughness, density, and mechanical properties remains a multi-objective optimization challenge.

Therefore, experimental investigation is required to

 ©IJSRED: All Rights are Reserved

identify the influence of process parameters and determine an optimized combination for producing high-quality SS316L components.

6. Research objectives

The main objectives of the proposed research are:

1. To study the Laser Powder Bed Fusion process and identify its important manufacturing parameters.
2. To investigate the effects of laser power, scanning speed, hatch spacing, and layer thickness on component quality.
3. To evaluate surface roughness, relative density, hardness, and tensile strength of manufactured specimens.
4. To identify the most influential process parameters using ANOVA.
5. To optimize the process parameters using Taguchi methodology and Response Surface Methodology.
6. To develop mathematical relationships between input parameters and output responses.
7. To validate the optimized process parameters experimentally.
8. To compare the optimized component properties with the baseline manufacturing conditions.

7. Literature review

The following studies provide a foundation for your research.

Author and year	Research area	Main contribution
Chia et al. (2022)	Metal AM parameter optimization	Review of optimization methods and process parameters
Ahmed et al. (2022)	LPBF of SS316L	Parameter selection, densification and microstructure
Diaz Vallejo et al. (2021)	LPBF of 316L	Process optimization and microstructural analysis
Oliveira et al. (2020)	LPBF process parameters	Effects of processing conditions on material properties
Nandhakumar and Venkatesan (2023)	SLM process parameters	Microstructure, tribological properties and surface roughness
Evangelou et al. (2023)	LPBF of 316L	Effect of scanning strategy and process parameters on density and microstructure

These studies show that the relationship between process parameters and final component quality is complex. In particular, laser power, scanning speed, hatch spacing, layer thickness, powder characteristics and scanning strategy should be considered together.

oaepublish.com+5

8. Research gap

This is one of the most important sections for journal publication.

Based on the reviewed literature, the following research opportunities can be investigated:

1. Many studies focus on individual responses such as density or surface roughness rather than considering several responses simultaneously.
2. The interaction effects of laser power, scanning speed, hatch spacing and layer thickness require further investigation for different machines and material batches.
3. There is scope to combine Taguchi methodology, ANOVA and RSM for systematic parameter optimization.
4. A comparison between predicted and experimentally validated optimum conditions can improve the reliability of optimization models.
5. There is scope to investigate the relationship between surface roughness, porosity, hardness and tensile strength under a common experimental design.

Proposed research gap statement for your paper:

Although considerable research has been conducted on the optimization of Laser Powder Bed Fusion parameters, the simultaneous optimization of surface roughness, relative density and mechanical properties remains a challenging task due to the complex interactions among process parameters. Therefore, the present research proposes an integrated experimental and statistical optimization approach to investigate the combined effects of major LPBF process parameters on the quality and performance of SS316L components. The study will also validate the predicted optimum conditions through experimental investigation.

Note: Treat this as a proposed research gap. A final novelty claim requires a systematic literature search and comparison with existing studies.

References:-

[1] J. P. Oliveira, A. D. LaLonde, and J. Ma, “Processing parameters in laser powder bed fusion metal additive manufacturing,” Materials & Design, vol. 193, Art. no. 108762, 2020. DOI: https://doi.org/10.1016/j.matdes.2020.108762

[2] N. Ahmed, I. Barsoum, G. Haidemenopoulos, and R. K. Abu Al-Rub, “Process parameter selection and optimization of laser powder bed fusion for 316L stainless steel: A review,” Journal of Manufacturing Processes, vol. 75, pp. 415–434, 2022. DOI: https://doi.org/10.1016/j.jmapro.2021.12.064

[3] “Factor analysis of selective laser melting process parameters with normalised quantities and Taguchi method,” Optics & Laser Technology, 2019.

[4] A. Evangelou, R. Stylianou, A. Loizou, D. Kim,

 ©IJSRED: All Rights are Reserved

A. Liang, P. Reed, G. Constantinides, and T. Kyratsi, "Effects of process parameters and scan strategy on the microstructure and density of stainless steel 316L produced via laser powder bed fusion," Journal of Alloys and Metallurgical Systems, vol. 3, Art. no. 100027, 2023. DOI: https://doi.org/10.1016/j.jalmes.2023.100027

[5] E. Amar, V. Popov, V. M. Sharma, S. A. Batat, D. Halperin, and N. Eliaz, "Response Surface Methodology (RSM) Approach for Optimizing the Processing Parameters of 316L SS in Directed Energy Deposition," Materials, vol. 16, no. 23, Art. no. 7253, 2023.

[6] S. Theeda, S. H. Jagdale, B. B. Ravichander, and G. Kumar, "Optimization of Process Parameters in Laser Powder Bed Fusion of SS 316L Parts Using Artificial Neural Networks," Metals, vol. 13, no. 5, Art. no. 842, 2023. DOI: https://doi.org/10.3390/met13050842

[7] M. Gor et al., "Experimental investigation on process parameters induced mechanical and microstructural properties for laser powder bed fusion additive manufacturing of SS316L," Proceedings of the Institution of Mechanical Engineers, Part E: Journal of Process Mechanical Engineering, 2023. DOI: https://doi.org/10.1177/09544089231191905

[8] "Melt Pool characteristics on surface roughness and printability of 316L stainless steel in laser powder bed fusion," Rapid Prototyping Journal, vol. 31, no. 10, pp. 2101–2118, 2025. DOI: https://doi.org/10.1108/RPJ-02-2024-0078

[9] "A comprehensive investigation on microstructure and mechanical properties optimisation of 316L stainless steel produced by laser-based powder bed fusion," Rapid Prototyping Journal. DOI: https://doi.org/10.1108/RPJ-12-2024-0519

[10] P. Dong, K. Jamkamon, and S. Chuvaree, "Influence and Optimization of Process Parameters on Surface Roughness of Selective Laser Melting of 316L Stainless Steel," Coatings, vol. 16, no. 1, Art. no. 134, 2026. DOI: https://doi.org/10.3390/coatings16010134

The publication details and research topics for references [1]–[10] can be checked against the publisher records.

[11] "The Effects of SLM Process Parameters on the Relative Density and Hardness of Austenitic Stainless Steel 316L," Journal of Materials Research and Technology, vol. 29, pp. 1616–1629, 2024. DOI: https://doi.org/10.1016/j.jmrt.2024.01.237

[12] "Influence of the Processing Parameters on the Microstructure and Mechanical Properties of 316L Stainless Steel Fabricated by Laser Powder Bed Fusion," Journal of Manufacturing and Materials Processing, vol. 8, no. 1, Art. 35, 2024.

[13] "Effect of Processing Parameters and Thermal History on Microstructure Evolution and Functional Properties in Laser Powder Bed Fusion of 316L," Materials & Design, vol. 244, Art. 113136, 2024. DOI: https://doi.org/10.1016/j.matdes.2024.113136

[14] V. B. Vukkum and R. K. Gupta, "Review on Corrosion Performance of Laser Powder-Bed Fusion Printed 316L Stainless Steel: Effect of Processing Parameters, Manufacturing Defects, Post-Processing, Feedstock, and Microstructure," Materials & Design, vol. 221, Art. 110874, 2022.

[15] "A Critical Review on Effect of Process Parameters on Mechanical and Microstructural Properties of Powder-Bed Fusion Additive Manufacturing of SS316L," Materials, vol. 14, no. 21, Art. 6527, 2021.

[16] "Data-Driven Performance-Oriented Rapid Process Optimization for 316 Stainless Steels Prepared by Laser Powder Bed Fusion," Metals, vol. 15, no. 9, Art. 968, 2025. DOI: https://doi.org/10.3390/met15090968

[17] "Experimental Study on Parameters Optimization of Selective Laser Melting 316L Stainless Steel Based on the Response Surface Methodology," Journal of Engineering Materials and Technology, 2024. DOI: https://doi.org/10.1115/1.4065426

[18] "A Comprehensive Investigation on Microstructure and Mechanical Properties Optimisation of 316L Stainless Steel Produced by Laser-Based Powder Bed Fusion," Rapid Prototyping Journal, 2026. DOI: https://doi.org/10.1108/RPJ-12-2024-0519

[19] "Influence and Optimization of Process Parameters on Surface Roughness of Selective Laser Melting of 316L Stainless Steel," Coatings, vol. 16, no. 1, Art. 134, 2026. DOI: https://doi.org/10.3390/coatings16010134

[20] "Melt Pool Characteristics on Surface Roughness and Printability of 316L Stainless Steel in Laser Powder Bed Fusion," Rapid Prototyping Journal, 2025. DOI: https://doi.org/10.1108/RPJ-02-2024-0078

[21] "Process Optimization and Microstructure Analysis to Understand Laser Powder Bed Fusion of 316L Stainless Steel," Metals, vol. 11, no. 5, Art. 832, 2021. DOI: https://doi.org/10.3390/met11050832

[22] "Predictive Modeling and Multi-Objective Optimization of SLM 316L Stainless Steel via Response Surface Methodology and Grey Relational Analysis," Applied Sciences, 2026.

[23] "Robust Multi-Objective Optimization of L-PBF Process Parameters for AISI 316L Using NSGA-II, TOPSIS, and Monte Carlo Simulation," Progress in Additive Manufacturing, 2026

 ©IJSRED: All Rights are Reserved